



Mineral Fiber Rubber Sheet

Code: KXITEB701

Description

Mineral Fiber Rubber Sheet is made from Mineral Fiber fiber, rubber and heat-resisting materials, compressing it into thick paper.



Item no.: KXITEB701

Mineral Fiber Rubber Sheet







Item no.: KXITEB701

- * Economical sheet
- * Wide range of pressure and temperature

Typical Application

- * Used for equipment in water, steam, etc.
- * Used as sealing material in the joint of pipeline

Technical Data

Mineral Fiber Rubber Sheet Physical Property						
GB/T539-1995						
Item	B70145	B70140	B70135	B70130	B70120	B70115
Color						
Tensile Strength \geq Mpa	19.0	15.0	12.0	9.0	6.0	5.0
Aging Coefficient \geq	0.9					
Burning loss \leq %	28		30		30	
Density g/cm ³	1.6~2.0					
Compressibility %	12+/-5					
Rebound Degree	45		40		35	
Pliability	No crack					
Stress relaxation \leq	50					
Steam Airtightness	With the temperature of 440~450oC	With the temperature of 390~400oC	With the temperature of 340~350oC	With the temperature of 290~300oC	With the temperature of 200~220oC	With the temperature of 140~150oC

Copyright © 2014-2015

Ningbo Kaxite Sealing Materials Co., Ltd.

No.134,Huancheng North Road,Jiangbei District,
Ningbo City,Zhejiang Province,China (Zip:315020)

Website:<http://www.seal-china.com> E-mail:sales@seal-china.com



Mineral Fiber Rubber Sheet

Code: KXITEB701

	and the pressure of 11~12Mpa, keep for 30 min without puncture	and the pressure of 8~9Mpa, keep for 30 min without puncture	and the pressure of 7~8Mpa, keep for 30 min without puncture	and the pressure of 4~5Mpa, keep for 30 min without puncture	and the pressure of 2~3Mpa, keep for 30 min without puncture	and the pressure of 1.5~2Mpa, keep for 30 min without puncture
--	--	--	--	--	--	--

Dimensions

4100x1500x(0.5~6.0)mm, 2000x1500x(0.5~6.0)mm

1500x1360x(0.5~6.0)mm, 3810x1270x(0.5~6.0)mm

1270x1270x(0.5~6.0)mm, 1500x1500x(0.5~6.0)mm

The other size is optional or according to the requirements of customers.

Copyright © 2014-2015

Ningbo Kaxite Sealing Materials Co., Ltd.

No.134,Huancheng North Road,Jiangbei District,
Ningbo City,Zhejiang Province,China (Zip:315020)

Website:<http://www.seal-china.com> E-mail:sales@seal-china.com